



FINEO is much more than glass technology. It is pure living comfort. This groundbreaking vacuum insulating glass not only delivers amazing energy performance, it also combines exceptional thermal insulation with unprecedent durability.

The thin vacuum insulating glass is elegant and sleek.

The Heritage range offers the best look-alike of the original glazing in heritage, historic buildings or period houses. Choose from a series of monumental glasses to match the historic character of the facade.

FINEO insulates as effectively as triple glazing but is lighter and thinner, meaning it can be installed into existing window frames. This often makes FINEO the most economical solution for renovation and restoration projects.

FINEO is a sustainable investment as it is 100% recyclable. It also has a long life expectancy without any loss of performance.



What's so special about it?	What does it mean for you?
Slim, sleek and aesthetical design	<ul> <li>An appearance similar to monolithic glass</li> <li>No vacuum evacuation port</li> <li>20 mm grid micro-pillars<sup>(1)</sup></li> <li>Suitable for retrofitting(*) into existing windows</li> </ul>
Outstanding thermal insulation	<ul> <li>U-value = 0,7 W/(m2.K)</li> <li>Regardless of the inclination (e.g. sloped or roof glazing)</li> </ul>
Sustainable investment	Designed to perform for several decades
More natural daylight	Slim design providing more light comfort inside
Harnessing more free solar energy	<ul><li>Lower energy consumption</li><li>Lower emissions</li></ul>
Better noise reduction	<ul><li>Increased soundproofing</li><li>Reduced traffic noise</li></ul>
Lead-free and recyclable	<ul><li>100% Recyclable</li><li>Circular sustainability</li></ul>
Reduced UV radiation	<ul><li>Blocks up to 99% of UV rays</li><li>Reduces discoloration of interior furniture</li></ul>

<sup>(\*)</sup> retrofitting: replace the existing glass with a FINEO glazing, fully preserving the initial window frame (provided the frame is in good condition).

## LESS IS MORE

The FINEO Heritage range offers a choice of six types of restoration glass suitable for historic buildings and homes. FINEO Heritage glass is the most suitable solution to preserve the visual aspect of the originally installed glass from the 1880s to the 1960s.

Period	FINEO Heritage Range
Around 1880	Traditional
1880 to 1920	Traditional Light
1920 to 1960	Classic Light, Classic, Classic Strong
From 1960	Modern



## LIGHT AND ENERGY PERFORMANCE(2)

	Total	EN 410				EN 673
FINEO HERITAGE	thickness [mm]	LT [%]	LR ext [%]	LR int [%]	g [-]	Ug [W/ (m².K)]
FINEO Heritage Modern 8	11.4	78	13	14	0.57	
FINEO Heritage Classic Light 8	11.3	78	13	14	0.58	
FINEO Heritage Classic 8	11.3	78	13	14	0.58	0.7
FINEO Heritage Classic Strong 8	11.5	78	13	14	0.57	0.7
FINEO Heritage Traditional Light 8	13.0	78	13	14	0.57	
FINEO Heritage Traditional 8	11.5	78	13	14	0.57	

## ACOUSTIC PERFORMANCE(3)

F. :	EN ISO 10140		
HERITAGE	Rw [C;Ctr] [dB]	Rw+Ctr [dB]	
FINEO Heritage 8	39 (-2;-4)	35	

## PRODUCTION FEASIBILITY

Dimensions	Maximum <sup>(4)</sup>	1.5m x 2.5m or 1.6m x 2.4m	
Dimensions	Minimum	0.2m x 0.2m	
Shapes	Available in an important number of shapes		
On demand	FINEO Traditional	Check stock availability before placing an order	

Missing or misplaced micro-pillars can occur. These misplaced or missing micro-pillars do not jeopardize the aesthetics (under normal obser-(1) vation conditions), the function, the performances nor the mechanical integrity over time of FINEO.



 $These \ data \ are \ calculated \ using \ spectral \ measurements \ compliant \ with \ standards \ EN\ 410 \ and \ ISO\ 9050\ (1990). \ The \ Uglass-value \ is \ calculated \ using \ spectral \ measurements \ compliant \ with \ standards \ EN\ 410 \ and \ ISO\ 9050\ (1990). \ The \ Uglass-value \ is \ calculated \ using \ spectral \ using \ spectral \ using \ spectral \ using \$ according to standard EN 673. Emissivity is measured as per standards EN 673 (Annex A) and EN 12898.

<sup>(3)</sup>  $These sound reduction indexes correspond to a FINEO sample measuring 1.23m \times 1.48m \ as per EN ISO 10140-3. The testing is carried out under the properties of the propertie$ laboratory conditions. In-situ performance may vary depending on the actual glazing dimensions, frame system, noise sources, etc.

The maximum dimensions depend on climatic conditions.